Ball & Doggett
ballanddoggett.com.au

Adestor

ADESTOR Fluo Yellow

FACESTOCK

Fluo Yellow

Description Matt coated woodfree paper with a yellow fluorescent coating.

Color Yellow

Applications Eye-catching labels for pricing, display, promotions and warning signs.

Printing techniques Suitable for printing on flexo (all types), letterpress (conventional and UV), hot stamping, laser, conventional offset, offset UV, screen printing, thermal transfer.

| Property | Norm | Units | Value | Tolerance |
|------------------------|--------------|-------|---------|--------------|
| Substance | ISO 536 | g/m² | 80 | 76-84 |
| Thickness | ISO 534 | μm | 82 | 77-87 |
| Bekk smoothness | ISO 5627 | s | 250 | ≥ 200 |
| Tensile strength MD/CD | ISO 1924 | kN/m | 5,5/2,6 | ≥ 4,5/ ≥ 2,2 |
| Flatness | TAPPI UM 427 | mm | ≤30 | |

Certificates

Product approvals and usage certificates

EN 71-3 Toy safety



 $[\]mbox{^{\circ}}$ Values are subject to change without notice. Last updated 5/10/2012.

[•] The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.

Ball & Doggett ballanddoggett.com.au

Adestor

ADESTOR A251

ADHESIVE

A251

Description General use acrylic permanent adhesive including smooth and slightly rough or curved surfaces.

Shelf life From the date of manufacture 2 years in 20°C and RH 50%

| Property | Norm | Units | Value | Tolerance |
|--|-------|--------|-------|-----------|
| Adhesion (Peel 180° 20'/stainless steel) | FTM 1 | N/25mm | 15,4 | ≥ 12,3 |
| Shear (1kg, in²/glass) | FTM 8 | min | 100 | ≥ 60 |
| Tack (Quick Stick stainless steel) | FTM 9 | N | 10,3 | ≥ 7,8 |
| Minimum labelling temperature | | °C | +5 | |
| Minimum service temperature | | °C | -20 | |
| Maximum service temperature. | | °C | +80 | |

Certificates

Product approvals and usage certificates

Packaging and packaging waste Directive 94/62/CE

EN 71-3 Toy safety

EN 71-9 Toy safety



Values are subject to change without notice. Last updated 7/28/2014.

The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.

Ball & Doggett
ballanddoggett.com.au

Adestor

ADESTOR WK80

LINER

WK80

Description One-side coated white liner with good lay-flat characteristics. Suitable for sheeting. Available only in solid back

Color White

| Property | Norm | Units | Value | Tolerance |
|------------------------|------------|-------|---------|-----------|
| Substance | ISO 536 | g/m² | 80 | ± 4% |
| Thickness | ISO 534 | μm | 81 | ± 4 |
| Tensile strength MD/CD | ISO 1924-2 | kN/m | 4,6/2,3 | -0,6/-0,3 |

Certificates

Product approvals and usage certificates

Contact with foodstuff (BfR XXXVI) - Facestock and Liners (paper)

Packaging and packaging waste Directive 94/62/CE

EN 71-3 Toy safety

Electric and electronic equipment (RoHS)



Values are subject to change without notice. Last updated 10/21/2016.

⁻ The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.

Ball & Doggett ballanddoggett.com.au

Adestor

ADESTOR WG62

ITNER

WG62

Super-calendered white translucent glassine paper especially designed for automatic labelling Description applications and photocell dispensing systems. This liner provides good tear resistance and smooth and regular thickness.

Color White

| Property | Norm | Units | Value | Tolerance |
|-----------|---------|-------|-------|-----------|
| Substance | ISO 536 | g/m² | 62 | 59-65 |
| Thickness | ISO 534 | μm | 52 | 49-55 |

Certificates

Product approvals and usage certificates

Contact with foodstuff (BfR XXXVI) - Facestock and Liners (paper)

Packaging and packaging waste Directive 94/62/CE

EN 71-3 Toy safety

Electric and electronic equipment (RoHS) Directive 2002/95/CE



Values are subject to change without notice. Last updated 11/26/2012.

The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.