

Product: Adestor Cast Gloss Removable

Adestor

Category: Folio Papers - Self Adhesive

Country of origin: Spain

Technical specifications:

FACESTOCK

High Gloss 80

Description Cast coated woodfree paper.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	80	± 4%
Thickness	ISO 534	µm	78	± 4%
Bekk smoothness	ISO 5627	s	1000	± 300
Brightness ISO	ISO 2470-2	%	89	± 2
Whiteness CIE	ISO 11475	%	108	± 5
Opacity	ISO 2471	%	92	-2
Paper gloss 20°	ISO 8254-3	%	41	± 4
Tensile strength MD/CD	ISO 1924-2	kN/m	4.3/2.7	± 0.7 / ± 0.5

ADHESIVE

RA678

Description Acrylic removable adhesive with clean removability from most surfaces. Trial is recommended when using this adhesive in new or unknown surfaces

Property	Norm	Units	Value	Tolerance
Adhesion (Peel stainless steel 1 week)	FTM 1	N/25mm	1,7	1 - 2,9
Shear (1kg, in ² /glass)	FTM 8	min	120	≥ 60
Tack (Quick Stick stainless steel)	FTM 9	N	1,2	0,7 - 1,7
Minimum labelling temperature		°C	5	
Minimum service temperature		°C	-20	
Maximum service temperature.		°C	+80	

LINER

WK80

Description One-side coated white liner with good lay-flat characteristics. Suitable for sheeting. Available only in solid back

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	80	±4%
Thickness	ISO 534	µm	81	±4
Tensile strength MD/CD	ISO 1924-2	kN/m	4,6 / 2,3	-0,6 / -0,3

Certificates

Product approvals and usage certificates

FACESTOCK

High Gloss 80

Electric and electronic equipment (RoHS) Directive 2002/95/CE

Contact with foodstuff (BfR XXXVI) - Facestock and Liners (paper)

EN 1230 Sensorial analysis

EN 71-3 Toy safety

Packaging and packaging waste Directive 94/62/CE

ADHESIVE

RA678

EN 71-3 Toy safety

Packaging and packaging waste Directive 94/62/CE

LINER

WK80

Contact with foodstuff (BfR XXXVI) - Facestock and Liners (paper)

Packaging and packaging waste Directive 94/62/CE

EN 71-3 Toy safety

Electric and electronic equipment (RoHS) Directive 2002/95/CE

-
- * Values are subject to change without notice. Last updated 6/8/2012.
 - * The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.