

Product: Adestor Matt Coated

Adestor

Category: Folio Papers - Self Adhesive

Country of origin: Spain

Technical specifications:

FACESTOCK

Matt 80

Description Matt coated woodfree paper.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	80	± 4%
Thickness	ISO 534	µm	74	± 4%
Bekk smoothness	ISO 5627	s	≤100	
Brightness ISO	ISO 2470-2	%	96	± 2
Whiteness CIE	ISO 11475	%	119	± 3
Opacity	ISO 2471	%	90	-2
Paper gloss 20°	ISO 8254-1	%	22	± 4%
Tensile strength MD/CD	ISO 1924-2	kN/m	4.3	-0.7

ADHESIVE

A251

Description General use acrylic permanent adhesive including smooth and slightly rough or curved surfaces.

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	15,4	≥ 12,3
Shear (1kg, in ² /glass)	FTM 8	min	100	≥ 60
Tack (Quick Stick stainless steel)	FTM 9	N	10,3	≥ 7,8
Minimum labelling temperature		°C	+5	
Minimum service temperature		°C	-20	
Maximum service temperature.		°C	+80	

LINER

WK80

Description One-side coated white liner with good lay-flat characteristics. Suitable for sheeting. Available only in solid back

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	80	±4%
Thickness	ISO 534	µm	81	±4
Tensile strength MD/CD	ISO 1924-2	kN/m	4,6 / 2,3	-0,6 / -0,3

Certificates

Product approvals and usage certificates

FACESTOCK

Matt 80

Contact with foodstuff (BfR XXXVI) - Facestock and Liners (paper)

EN 1230 Sensorial analysis

Toy safety European directive 2009/48/CE

Packaging and packaging waste Directive 94/62/CE

Electric and electronic equipment (RoHS) Directive 2002/95/CE

ADHESIVE

A251

Packaging and packaging waste Directive 94/62/CE

EN 71-3 Toy safety

EN 71-9 Toy safety

Direct contact with foodstuffs (ISEGA) - Adhesives

LINER

WK80

Contact with foodstuff (BfR XXXVI) - Facestock and Liners (paper)

Packaging and packaging waste Directive 94/62/CE

EN 71-3 Toy safety

Electric and electronic equipment (RoHS) Directive 2002/95/CE

* Values are subject to change without notice. Last updated 6/5/2012.

* The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.