

# Technical specification sheet

Ball & Doggett

ballanddoggett.com.au

**Product:** JAC EcoPlus White Gloss

**Category:** Folio Papers - Self Adhesive

**Country of origin:** Germany

## Technical specifications:

### Print carrier

### Average values

**JAC<sup>®</sup> ECOPLUS** is a series of environmentally friendly<sup>3)</sup> phthalate-free<sup>2)</sup> polyolefin films for sheet printers. All films display excellent printability thanks to a printer-friendly top coating. Printing tests have produced very good results when

**Offset-printed:** with both purely oxidative drying and UV-curing inks, and

**Screen-printed:** with conventional (i.e. solvent-based) and UV-curing inks.

Consult your printing ink manufacturer or supplier about suitable printing inks for your applications. Tests have shown that **JAC ECOPLUS** performs well in semi-automatic and fully automatic screen and offset printing machines, whereby the laminate displays optimal stability flatness. All **JAC ECOPLUS** films display good die-cutting properties.

#### Available articles:

**JAC<sup>®</sup> 60600** – transparent gloss PP film, top coated

**JAC<sup>®</sup> 62600** – white gloss PP film, top coated

Type No.	60600	62600
Weight (g/m <sup>2</sup> )	54	58
Thickness (µm)	59	59
Tensile strength		
longitudinal (N/15mm)	200	175
transverse (N/15mm)	180	155
Transparency (%)	90	
Opacity (%)		80
Shelf life of laminate (years) <sup>1)</sup>	2	2
Max. outdoor durability (years) <sup>4)</sup>	**	**

\*\* Material is recommended for short term outdoor applications

<sup>1)</sup> Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50 ± 5% RH.

<sup>3)</sup> Environmentally friendly because the manufacture, processing and disposal of the film does not cause any serious environmental pollution. Incineration does not give off any toxic chlorine compounds such as dioxin or furan. Polyolefins are inert plastics, i.e. they do not readily react with other materials and can therefore be safely deposited as waste.

<sup>4)</sup> Under normal climatic conditions as prevailing in Central Europe.

For additional information regarding EHS regulations<sup>2)</sup> and technical guidance please visit our website under downloads "Guidelines for Use" - Screen Printing

### Adhesive

### Average values

**DURO D500** is a dispersion-based permanent acrylic adhesive that has been specially developed for polyolefin films.

**NONPERM C3** is a removable, dispersion-based acrylic adhesive specially developed for use with polyolefin films.

This transparent adhesive is distinguished by extreme heat and cold resistance coupled with high UV stability. It can be removed from most surfaces without leaving any residues.

#### Note!

JAC<sup>®</sup> ECOPLUS is recommended only for dry application.

	Duro D500	Nonperm C3
Adhesion (N/25mm)		
(FTM 1 on steel after 24h)	10	2.5
Tack (N/25mm)		
(FTM 9 on glass)		
Recommended minimum application temperature (°C) <sup>1)</sup>	> +5	> +5
Heat resistance <sup>1)2)</sup>		
up to 24h (°C)	+80	+80
up to 1h (°C)	+110	+110
Resistance to cold (°C) <sup>1)</sup> down to	-40	-40

<sup>1)</sup> Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

<sup>2)</sup> Heat resistance refers only to adhesive applied on steel. Quality of front material can be affected when exposed to higher temperatures.

### Silicone paper

### Average values

**B 145** is a siliconized, special-purpose lightweight board, wood-free, matt on reverse side, moisture-stabilized through specially impregnated fibres and special coating, hence its excellent flatness.

**B 145 SPLIT** is as above, but with scored lines running in machine direction serving as a peel-off aid.

	B 145
Basis weight (g/m <sup>2</sup> )	135
Caliper (µm)	127

#### Guarantee and liability

All Avery Dennison and JAC<sup>®</sup> statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison and JAC<sup>®</sup> products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All Avery Dennison and JAC<sup>®</sup> products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>