

Product: Apmil Bleached Kraft Counter Rolls - Machine Glazed

Category: Packaging - Food Service

Mill: Maryvale

Country of Origin: Australia

Technical specifications:

Description of Product:

This white coloured product has a Machine Glazed finish to allow enhanced print quality.

Mill:

Maryvale, Paper Machine 2 (M2).

Grammages:

Product is available at 33, 35, 37, 44, 49 and 55gsm

Certification:

The pulp and paper mill has the following certifications;

- Quality System AS/NZ ISO 9001:2008
- Environmental System AS/NZ ISO 14001:2004
- OH&S AS/NZS 4801:2001
- AFCS (PEFC) AS 4707-2006 Chain of Custody – See logo below

Materials:

The product is manufactured from a blend of virgin kraft fibres.

Food Contact Safety:

Suitability for use is guided by USFDA and European Regulation(BGVV, Council of Europe) requirements.

- ***This product is recommended as safe for use in contact with all food types.***

Customer Responsibilities:

Our customers must ensure that food safety compliance is maintained through their storage, handling and conversion processes.

This Product Sheet is regularly updated. Please ask your Australian Paper representative for latest version.

Other:

The delivered reels outer surface coincides with the Machine Glazed (MG) of the sheet.

The table below displays typical values. Test climate: RC @ 50%RH, 23° C. Grammage is as made.

Property	Unit	Typical Values						Method based on	
Grammage, as made	gsm	33	35	37	44	49	55	AS 1301.405s	
Moisture	%	6.5	5.5	6.5	6.5	6.5	6.5	AS 1301.457s	
Thickness	µm	47	50	52	61	67	74	AS 1301.426s	
Burst	kPa	145	160	170	210	230	260	AS 1301.400s	
Tensile	MD	kN/m	3.2	3.5	3.6	4.3	4.8	5.3	ISO 1924-3
	CD	kN/m	1.5	1.7	1.8	2.1	2.3	2.6	
Tear	MD	mN	235	255	275	335	380	440	AS 1301.400s
	CD	mN	255	275	295	365	420	480	
Roughness(Bendtsen)	TS	ml/min	530	540	560	620	670	720	AS 1301.439s
	MG	ml/min	100	100	110	110	120	120	AS 1301.439s
Porosity (Bendtsen)		ml/min	250	250	250	250	250	300	AS 1301.440s
Cobb, 1 min (multisheet)		gsm	28	28	28	28	28	28	AS 1301.411s
Gloss	MG	%	13.5	14.0	13.5	14.0	14.0	14.5	Tappi T480
Brightness	MG	D65/10°	83.0	83.0	83.0	83.0	83.0	83.0	AS 1301.446s
Opacity		%	57	58	60	64	67	71	AS 1301.454s

MD = Machine Direction CD = Cross Direction TS = Top Side MG = Machine Glazed RC = Rapid Conditioned



PEFC™

PEFC/21-31-08
Promoting sustainable forest management
For more info: www.pefc.org