

2) LUXLINE S

Indication of technical data

Product	Thickness fix (mm)	Substance Typical value (g/m ²)	Stiffness MD dynamic (mNm) ISO 5629	Stiffness CD dynamic (mNm) ISO 5629
2.a Unlined / Wood free offset	0,90	576	200	95
	1,00	640	265	135
	1,10	704	300	189
	1,20	768	430	225
	1,30	832	500	275
	1,40	896	600	325
2.c Wood free offset white / Unlined	1,00	640	265	135
2.e Grey / Wood free offset	1,00	640	348	160
	1,20	768	570	245
	1,30	832	525	220
	1,40	896	760	310
	1,50	960	920	405
	1,60 *	1.024	1.025	440
	1,70 *	1.088	1.165	475
	1,80 *	1.152	1.350	575
	1,90 *	1.216	1.500	635
	2,00 *	1.280	1.650	700
2.i 2-sides woodfree offset	1,00	670	350	180
	1,25	837,5	700	300
	1,50 *	1.005	900	400
	1,60 *	1.072	1.025	440
	1,90 *	1.273	1.500	635
2.k Unlined / Black	1,00	640	265	135
	1,20	768	430	225
	1,30	832	500	275
	1,40	896	600	325
	1,50	960	675	350
2.m Black / Unlined	0,90	576	200	95
	1,00	640	265	135
2.o Grey / Black	1,75	1.120	1.300	575
	2,00	1.280	1.650	700
2.r Black / Wood free offset	1,20	804	430	225
Moisture (%)			8,25	
Tolerance Moisture (%)			+/- 1	
Tolerance Thickness (%)			+/- 3	
Plybond DIN 54516 (N/min)			40	
Machine width (cm)			215 - 230 cm / 263-274 cm*	
FSC Certificate (Claim)			FSC® mix 70% CU-COC-810587	